

ALUJET Alucral

Productdiscription ALUJET Alucral adhesive tape is used to make airtight joints at overlapping areas of vapour check membranes. Through the use of a solvent-free acrylate dispersion, joints are possible from -10°C upwards. If ALUJET Alucral adhesive tape is used correctly, a vapour check function is also ensured in the overlapping area.



Product According DIN 4108-11 (Klebeband KB); extremely high adhesive strength; modified acrylate dispersion; solvent-free; handy dimensions.

Area of
applicationCommercially-available vapour checks; wood; hard wooden composite boards; gypsum
plasterboards.

| Technical data | Test | Standard | Unit | Value |
|----------------|---|-------------------------------------|-----------|-------------------|
| | Substrate | | | Special paper |
| | Adhesive | | | Acrylat |
| | Backing | | | Siliconised paper |
| | Temperature resistance | | °C | -40 bis +90 |
| | Processing temperature | | °C | From 5 upwards |
| | Thickness | DIN EN 1942 | mm | 0,29 ±0,05 |
| | Elongation | DIN EN 14410 | % | >5 |
| | Breaking force | DIN EN 14410 | N / 10 mm | 65 |
| | Adhesion on steel | DIN EN 1939 | N / 10 mm | 14 |
| Specification | Roll width: Roll length: Carton content: Palette content | 60mm 41m 8 rolls 54 carton | | |

Storage At approx. 15 °C to 30 °C and max. 65% rel. humidity.







Our instructions for use, guidelines for use, product and service information and other technical specifications only serve as a guide, they only describe the properties of our products (value specifications/determinations at time of production) and services and do not constitute guaranteed characteristics. Owing to the wide-ranging areas of application of the individual products and the particular conditions (e.g. usage parameters, material properties etc.), it is incumbent on the user to test our products. Our applications engineering consulting - whether verbal, in writing or by way of tests is offered free of charge and is not legally binding.